


► **WERKSTOFF / MATERIAL**

Metallgraphit / *metal graphite*

► **WERKSTOFFDATEN / MATERIALS DATA**


Dichte / <i>bulk density</i>	(DIN IEC 60413/203)	4.3 g/cm³
Rockwell-Härte / <i>Rockwell hardness</i> HR _{10/60}	(DIN IEC 60413/303)	90
Biegefestigkeit / <i>flexural strength</i>	(DIN IEC 60413/501)	30 N/mm²
spezif. elektr. Widerstand / <i>specific electr. resistance</i>	(DIN IEC 60413/402)	0.8 μΩm

► **LAUFEIGENSCHAFTSMERKMALE / OPERATIONAL CHARACTERISTICS**



Spannungsabfall ΔU [V]
von Bürste zu Bürste bei $v = 30$ m/s

Voltage drop ΔU [V]
from brush to brush at $v = 30$ m/s



Reibbeiwert μ
bei Stromdichte von 10 A/cm²

Coefficient of friction μ
at current density of 10 A/cm²

- Das elektrische und mechanische Verhalten wurde auf einem Bronzeschleifring SnBz 10 bei 70°C mit zwei Bürsten $t \cdot a = 8 \cdot 10$ mm und einem Anpreßdruck $p = 3.5$ N/cm² gemessen.
Voltage drop and coefficient of friction were measured on a bronze slip ring SnBz 10 at 70°C with two brushes $t \cdot a = 8 \cdot 10$ mm and brush pressure $p = 3.5$ N/cm².

► **ÜBLICHE BETRIEBSWERTE / USUAL OPERATION CONDITIONS**

Stromdichte / <i>current density</i>	./.
Gleitgeschwindigkeit / <i>peripheral speed</i>	20 m/sec
Bürstenanpreßdruck / <i>brush pressure</i>	3.5 N/cm²

► **EMPFEHLUNG FÜR DIE ANWENDUNG / RECOMMENDED APPLICATION**

Übertragung von Meßströmen *transfer low voltage signals*

Diese Angaben sollen über unsere Produkte und deren Anwendungsmöglichkeiten informieren. Sie haben somit nicht die Bedeutung, bestimmte Eigenschaften der Produkte oder deren Eignung für einen konkreten Einsatzzweck zuzichern.

This information is intended to provide general notes on our products and their uses. It should not therefore be construed as guaranteeing specific properties of the products described or their suitability for a particular application.

PanTrac GmbH

Vulkanstraße 13 · D-10367 Berlin · Germany

Telefon / Phone +49-30 55497 - 106

Telefax / Fax +49-30 55497 - 300

central@pantrac.com · www.pantrac.com